# NARMASK 340

INFORMATIVE DATA SHEET

## MASKING

### COMPOSITION

BACKING: lightly crepe paper ADHESIVE: natural rubber / hydrocarbonic resins / solvent CORE: recycled paper and paperboard

### SUITABLE FOR

Building sector for painting; decorative and industrial coatings; car bodywork and protective masking in general

### AVAILABLE COLOURS

White - yellow

The technical characteristics of the product make it resistant to humidity, to solvents and to temperatures application. The tape has high conformability and good mechanical resistance, it cuts easily and leaves no adhesive residues after removal. The product has a wide range of applications in the building sector for painting, decorative coatings, car bodywork and for protective masking in general.



BACKING WEIGHT 55 g/m<sup>2</sup>



ADHESION > **2,2 N/cm** 

BREAKING LOAD > **27 N/cm** 



NAR S.P.A. Legnaro (PADOVA) ITALY www.nar-spa.com



COMPANY WITH QUALITY SYSTEM CERTIFIED BY DNV GL = ISO 9001:2015 = LEGNARO - SCHIO - BRUGINE COMPANY WITH ENVIRONMENTAL SYSTEM CERTIFIED BY DNV GL = ISO 14001:2015 = LEGNARO COMPANY WITH ENERGY MANAGEMENT SYSTEM CERTIFIED BY DNV GL = ISO 50001:2011= LEGNARO





RESIDUAL FREE REMOVAL



INFORMATIVE DATA SHEET

			$\sim$	N. C.		°C	°C	*		
	backing weight g/m²	total thickness µm	adhesion N/cm	breaking load N/cm	elongation at break %	heat resistance for 90 min.	heat resistance for 30 min.	easy cut	UV resistant	residual free removal
NARMASK 340	55	125	> 2,2	> 27	> 8	55° C	70° C	•		•
NARMASK 360	58	130	> 2,3	> 32	> 8	60° C	80° C	•		•
NARMASK 380	76	145	> 2,3	> 35	> 8	60° C	80° C	•		•
NARMASK UVR 380	76	145	> 2,3	> 35	> 8	60° C	80° C	•	•	•
NARCAR 350	58	135	> 2,6	> 32	> 8	80° C	110° C	•		•
NARCAR 380	76	150	> 2,6	> 35	> 8	80° C	110° C	•		•

It is good practice to use the product within 12 months from purchase date (6 months if jumbo roll). The rolls must be kept in their original packing. Keep the product out of the light and protect from direct heat sources. The tape must be kept in a dry place, at humidity level below 65%, preferably at a temperature between 15° C and 25° C. If the storage temperature is different, restore the tape back to above level before using it.

The values in the informative data sheets are the average results of tests made on our standard production and are not legally binding. The aesthetic and technical features may be subject to some changes caused by ageing, even though the quality level of the product is maintained. Nar shall not be liable for direct damages or for any consequence arising from the misuse of the product. We suggest the verification of the product suitability to the specific condition of use.



Additional indications are available in the last edition of the booklet "Recommendation regarding choice, storing and use of pressure sensitive tapes" published by Federazione Gomma Plastica.